

COLLECTION: **DELUXE**

DESIGN: **DELUXE**

## BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	53
Tariff item number	6001920000	MID	CNJIABRI366TON
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	25
Full roll diameter inch	9.84	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

## CARE AND USAGE

Care code comments

Iron on reverse side

### Care codes



### Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

## ENVIRONMENTAL STANDARDS

**ISO 14001**

Environmental  
Management



STANDARD  
100

0611045  
Centexbel

PFC-free	Yes
----------	-----

## FR STANDARDS

British BS 5852 source 0	Yes	American CAL 117	Yes
MVSS 302	Yes	American NFPA 260	Yes

COLLECTION: **DELUXE**

DESIGN: **DELUXE**

## FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	33.41
Construction	knitted	Useable width cm	141
Useable width inch	55.51	Full width cm	143
Full width inch	56.3	Weight g/m <sup>2</sup>	419
Thickness mm	1.190	Colouring type	Printed
Filament or staple	100% filament	Textured or non textured	100% not textured

### Treatment

Backing	Yes	Stain free technology	Yes
PFC free	Yes		

### Type of finish

Thermofixed	Yes
-------------	-----

### Type of print or dye

Disperse	Yes
----------	-----

### Weaving type

Pile	Yes
------	-----

## FABRIC TYPE

There are no technical details for this section.

COLLECTION: **DELUXE**

DESIGN: **DELUXE**

## MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	4
Wyzenbeek double rubs	200,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	200,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

### Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

### Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

### Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

### Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4
-------------------------	---

### Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

### Tearing strength - ISO 13937-3

Tearing strength warp N	75	Tearing strength weft N	82
-------------------------	----	-------------------------	----

### Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	560	Tensile strength weft N/5cm	630
-----------------------------	-----	-----------------------------	-----

### Elongation - ISO 13934-1

Elongation warp %	42	Elongation weft %	17
-------------------	----	-------------------	----

### Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

### Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.12	Dimensional change warp after ironing with steam	0.33
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.27	Dimensional change weft after ironing without steam	0.07

COLLECTION: **DELUXE**

DESIGN: **DELUXE**

## WASHABILITY

### Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.17	Dimensional change warp after ironing	-0.13
Dimensional change weft	0.13	Dimensional change weft after ironing	0.20
Colour fastness ISO 105 C06	5		

### Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.30	Dimensional change warp after ironing	-1.19
Dimensional change weft	0.03	Dimensional change weft after ironing	0.13
Colour fastness ISO 105 C06	5		

### Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.10	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 D01	5		

## CONSTRUCTION

### Yarn 1

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	105d
Weft Threads per cm	50	Weft TPM	300

### Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	105d
Warp Threads per cm	90	Warp TPM	200

## DOWNLOADS / CERTIFICATES

 [Deluxe – FibreGuard report](#)



COLLECTION: **DELUXE**

DESIGN: **DELUXE**

