

COLLECTION: **INDULGE**

DESIGN: **INDULGE**

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	30
Tariff item number	6001920000	MID	CNZHETONTON
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	25
Full roll diameter inch	9.84	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE AND USAGE

Care code comments

Iron on reverse side

Care codes



Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



**STANDARD
100**

0611045
Centexbel

PFC-free	Yes	Prop 65	Yes
----------	-----	---------	-----

FR STANDARDS

British BS 5852 source 0	Yes	British BS 5852 source 1	Yes
British BS 5852 source 1 comment	Yes, with FR coating	American CAL 117	Yes
MVSS 302	Yes	American NFPA 260	Yes

COLLECTION: **INDULGE**

DESIGN: **INDULGE**

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	
Construction	knitted velvet	Useable width cm	140
Useable width inch	55.12	Full width cm	142
Full width inch	55.91	Weight g/m ²	425
Thickness mm	1.580	Colouring type	Piece dyed
Filament or staple	100% filament	Textured or non textured	100% textured
Other treatment specification	embossed		

Treatment

Backing	Yes	Stain free technology	Yes
PFC free	Yes	Other treatment	Yes

Type of finish

Sanforized	Yes
------------	-----

Weaving type

Pile	Yes
------	-----

FABRIC TYPE

There are no technical details for this section.

COLLECTION: **INDULGE**

DESIGN: **INDULGE**

MECHANICAL PERFORMANCE

Martindale rubs	20,000	Colour fastness to light	3-4
Wyzenbeek double rubs	150,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	150,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	3-4
--------------------------	-----

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	3-4
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strength warp N	75	Tearing strength weft N	34
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	1100	Tensile strength weft N/5cm	240
-----------------------------	------	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	63	Elongation weft %	68.5
-------------------	----	-------------------	------

Seam slippage - ISO 13936-2

Seam slippage warp mm	3	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.07	Dimensional change warp after ironing with steam	0.86
Dimensional change warp after ironing without steam	0.20	Dimensional change weft	0.15
Dimensional change weft after ironing with steam	-0.47	Dimensional change weft after ironing without steam	0.07

COLLECTION: **INDULGE**

DESIGN: **INDULGE**

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.70	Dimensional change warp after ironing	-0.60
Dimensional change weft	0.37	Dimensional change weft after ironing	0.40
Colour fastness ISO 105 C06	4		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.43	Dimensional change warp after ironing	-2.20
Dimensional change weft	0.73	Dimensional change weft after ironing	0.80
Colour fastness ISO 105 C06	4		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.12	Dimensional change warp after ironing	0.86
Dimensional change weft	0.73	Dimensional change weft after ironing	0.86
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION


Yarn 1


Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Textured	Yes	Warp Sizes	75D/144F
Warp Textured	Yes	Warp Threads per cm	

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Textured	Yes	Weft Sizes	75D/144F
Weft Textured	Yes	Weft Threads per cm	

DOWNLOADS / CERTIFICATES

 [Indulge – FibreGuard report](#)

 [Indulge – FibreGuard report](#)



COLLECTION: **INDULGE**

DESIGN: **INDULGE**

