

COLLECTION: **KEYSTONE**

DESIGN: **KEYSTONE**

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	35
Tariff item number	5211310090	MID	INDEHOM167MUM
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	23.5
Full roll diameter inch	9.25	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE AND USAGE

Care codes



Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



**STANDARD
100**
0611045
Centexbel

FR STANDARDS

British BS 5852 source 0	Yes	British BS 5852 source 1	Yes
British BS 5852 source 1 comment	Yes, with FR coating	American CAL 117	Yes
MVSS 302	Yes	American NFPA 260	Yes

COLLECTION: **KEYSTONE**

DESIGN: **KEYSTONE**

FABRIC SPECIFICATIONS

Composition	79% Cotton, 21% Polyester	Average yarn number	6.79
Construction	14.17x9.06	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	342	Thickness mm	0.850
Colouring type	Piece dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

Stain free technology Yes

Type of finish

Sanforized Yes Stenter Yes

Type of print or dye

Reactive Yes

Weaving type

Dobby Yes

FABRIC TYPE

There are no technical details for this section.

COLLECTION: **KEYSTONE**

DESIGN: **KEYSTONE**

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	4
Wyzenbeek double rubs	20,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	20,000	Wyzenbeek cotton duck type unrated	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	4-5
--------------------------	-----

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	62	Tearing strength weft N	91
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	1400	Tensile strength weft N/5cm	790
-----------------------------	------	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	17	Elongation weft %	16
-------------------	----	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing with steam	-0.20
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	-0.07

COLLECTION: **KEYSTONE**

DESIGN: **KEYSTONE**

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.10	Dimensional change warp after ironing	-1.99
Dimensional change weft	-2.23	Dimensional change weft after ironing	-2.00
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.92	Dimensional change warp after ironing	-2.32
Dimensional change weft	-2.52	Dimensional change weft after ironing	-2.32
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Warp Composition	79% Cotton, 21% Polyester	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	1100D
Warp Threads per cm	14.17	Warp TPM	0

Yarn 2

Weft Composition	79% Cotton, 21% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	1100D
Weft Threads per cm	9.06	Weft TPM	0

DOWNLOADS / CERTIFICATES

[📄 Keystone – FibreGuard report](#)

[📄 Keystone – FibreGuard report](#)



