

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	38
Tariff item number	5514230000	MID	INDDEEXP167MUM
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	22
Full roll diameter inch	8.66	Average piece length m	40
Minimum for special colour m		Delivery time weeks special lab dip	2

CARE AND USAGE

Care codes



Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

FR STANDARDS

British BS 5852 source 0	Yes	American CAL 117	Yes
MVSS 302	Yes	American NFPA 260	Yes

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

FABRIC SPECIFICATIONS

Composition	73% Polyester, 27% Cotton	Average yarn number	9.25
Construction	20.5x19	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	427	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

Stain free technology Yes

Type of finish

Stenter Yes

Weaving type

Dobby Yes

FABRIC TYPE

There are no technical details for this section.

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	4
Wyzenbeek double rubs	90,000	Pilling	3-4
Brush pilling	3-4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	90,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	200	Tearing strength weft N	240
-------------------------	-----	-------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	840
-----------------------------	------	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	32.5	Elongation weft %	30.5
-------------------	------	-------------------	------

Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.19	Dimensional change warp after ironing with steam	-0.13
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.60	Dimensional change weft after ironing without steam	0.00

COLLECTION: **COLOURWASH**

DESIGN: **COLOURWASH**

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.80
Dimensional change weft	-0.63	Dimensional change weft after ironing	-0.53
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.96	Dimensional change warp after ironing	-1.79
Dimensional change weft	-0.80	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	0.37	Dimensional change warp after ironing	0.33
Dimensional change weft	-0.10	Dimensional change weft after ironing	0.33
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION


Yarn 1

Warp Composition	85% Polyester, 15% Cotton	Warp Is Staple	Yes
Warp Sizes	2/16	Warp Threads per cm	20.5
Warp TPM	500		

Yarn 2

Weft Composition	55% Polyester, 45% Cotton	Weft Is Staple	Yes
Weft Sizes	2/10	Weft Threads per cm	19
Weft TPM	210		

DOWNLOADS / CERTIFICATES

 [Colourwash – FibreGuard report](#)



COLLECTION: COLOURWASH

DESIGN: COLOURWASH

