

COLLECTION: **SUPERVIO**

DESIGN: **SUPERVIO**

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	35
Tariff item number	6001920000	MID	CNZHETONTON
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	34
Full roll diameter inch	13.39	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2
Suspended box	Yes		

CARE AND USAGE

Care code comments Iron on reverse side

Care codes



Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental Management



STANDARD 100

0611045 Centexbel

PFC-free	Yes	Prop 65	Yes
----------	-----	---------	-----

FR STANDARDS

AATCC 96 Complies	No	British BS 5852 source 0	Yes
British BS 5852 source 1	Yes	British BS 5852 source 1 comment	Yes, with FR coating
American CAL 117	Yes	MVSS 302	Yes
American NFPA 260	Yes		

COLLECTION: **SUPERVIO**

DESIGN: **SUPERVIO**

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	6.8
Construction	knitted	Useable width cm	138
Useable width inch	54.33	Full width cm	140
Full width inch	55.12	Weight g/m ²	500
Thickness mm	1.580	Colouring type	Piece dyed
Filament or staple	100% Filament	Textured or non textured	100% Textured

Treatment

Anti-bacterial/microbial	Yes	Mildew resistant	Yes
Odour resistant	Yes	Stain free technology	Yes
PFC free	Yes		

Type of finish

Sanforized	Yes
------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Pile	Yes
------	-----

FABRIC TYPE

There are no technical details for this section.

COLLECTION: **SUPERVIO**

DESIGN: **SUPERVIO**

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	No	Martindale rubs	100,000
Colour fastness to light	4	Wyzenbeek double rubs	100,000
Pilling	5	Brush pilling	4-5
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	100,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	3
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	38	Tearing strength weft N	72
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	630	Tensile strength weft N/5cm	510
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	70	Elongation weft %	58
-------------------	----	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.26	Dimensional change warp after ironing with steam	-0.80
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	-20.08
Dimensional change weft after ironing with steam	-0.20	Dimensional change weft after ironing without steam	0.07

COLLECTION: **SUPERVIO**

DESIGN: **SUPERVIO**

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.86	Dimensional change warp after ironing	-0.99
Dimensional change weft	-0.36	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.21	Dimensional change warp after ironing	-2.18
Dimensional change weft	-2.05	Dimensional change weft after ironing	-1.92
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.01	Dimensional change warp after ironing	-1.26
Dimensional change weft	-1.39	Dimensional change weft after ironing	-1.26
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	75D/144F	Warp Textured	Yes
Warp Threads per cm	17	Warp TPM	25

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	30D/12F,40D Spandex	Warp Textured	Yes
Warp Threads per cm	17	Warp TPM	25

DOWNLOADS / CERTIFICATES

 [Supervio – FibreGuard report](#)



COLLECTION: **SUPERVIO**

DESIGN: **SUPERVIO**

